

Melting viscosity of GX13, GX92 & GXT31

“Ajinomoto Build-up film”

Variety	Min. melting viscosity	
	Poise	degC
GX13	1900	135
GX92	3700	131
GXT31	3600	129

The same facility and laminate condition is applicable for all variety.

