




Surface morphology after desmear

“Ajinomoto Build-up film”

Variety	GX13	GX92	GXT31
Cure	180degC*30 min	100degC*30min+ 180degC*30 min	100degC*30min+ 170degC*30 min
Desmear	Swell 60degC*5min, 80degC*20min		
SEM x3500			
Peel Strength	0.7-0.9kgf/cm	0.6-0.8kgf/cm	0.5-0.6kgf/cm