

TH Plugging by GX92R

Test Condition

- ◆ “Ajinomoto Build-up film”
Variety: GX92R (40um)
- ◆ Test board
TH substrate (0.3mmt, TH ϕ 250um, pitch 500um)
- ◆ Procedure
 1. Lamination:
1st: 100deg.C, 30s vac., 30s rubber press, +7kgf/cm² Air
2nd: 100deg.C, 60s, SUS press, 5.5kgf/cm²
 2. Curing : w/ PET and w/o PET,
100deg.C*60min.+180deg.C*30min.

Results

Cure	Depth of dent
w/o PET	11.1um
w/ PET	9.4um

